

1 **Photocatalytic degradations of malachite green on**
2 **magnetically separable $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles synthesized**
3 **by using a hydrothermal process**

4 *H- Y. He*

5 *College of Material Science and Engineering, Shaanxi University of Science and Technology, Xi'an, Shaanxi,*
6 *China(710021)*

7
8 **Abstract:** $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ ($x=0-1.0$) ferrite nanoparticles were synthesized by using a
9 hydrothermal process. The nanoparticles had average particle sizes of 14.8–29.4 nm
10 and a narrow band gap of 1.75–1.91 eV, decreasing with increasing Co content. The
11 nanoparticles showed an excellent sunlight-excited photocatalytic activity to
12 malachite green in water. Moreover, the addition of a small amount of H_2O_2 resulted
13 in an obviously enhanced photodegradation, indicating a Fenton-like reaction. The
14 photodegradation and Fenton-like photodegradation rates increased with increasing
15 Co content. Complete Co substitution for Ni resulted in an optimal effect.
16 Quasi-kinetic rate constant k values were in the range of $2.23-7.2 \times 10^{-2} \text{ min}^{-1}$ and
17 increased to $1.3-6.0 \times 10^{-1} \text{ min}^{-1}$ upon the addition of H_2O_2 . The measurement of
18 oxidation-reduction potential of the nanoparticles in the photodegradation condition
19 indicated a reductive characteristic enhanced with increasing Co content. Furthermore,
20 the nanoparticles possessed high saturation magnetizations of 50.7–64.2 $\text{emu} \cdot \text{g}^{-1}$ and
21 low coercivity of 0.4–1.7 kOe, which ensured that they gave magnetic separable in
22 finally degraded dye aqueous solution.

Keywords: Nanostructure; semiconductors; dye photodegradation; Fenton-like reaction; magnetic separation

1. Introduction

Photocatalysis plays an important role in dealing with today's challenging demand for decontamination of environment. For this purpose, nano-TiO₂ as a photocatalyst has been widely studied because of its excellent chemical stability and photocatalytic activity. To fully utilize sunlight and enhance the photocatalytic activity of nano-photocatalyst, developing photocatalyst with narrower band gap semiconductor than pure TiO₂ should be of interest. In some cases, such as waste water treatment, photocatalyst nanoparticles are also required to be separated from the photodegraded aqueous solution after the photodegradation process is completed. Magnetic separation is generally believed to be an effective technique.

Spinel ferrites have narrow band gap (~2.0 eV), so their nanoparticles could be potential photocatalysts for decontamination of environment because of their superiority in full utilization of natural sunlight. Moreover, this type of ferrites are ferrimagnetic and thus magnetic separable from aqueous solution. Previous studies have shown the excellent photocatalytic activity of some ferrite nanoparticles [1, 2]. Recent studies further indicated that the composites of different ferrites [2] and ferrite with other photocatalysts [3, 4] have higher efficiency than single ones. Different metal cations have different physical chemical behavior. Thus, it is necessary to investigate the effect of Co substitution for Ni on photocatalytic activity of nickel

45 ferrite nanoparticles.

46 In recent years, advanced oxidation processes (AOPs) by using UV/H₂O₂ have
47 become a way to degrade organic compounds in dilute solutions. In general, it is
48 believed that the UV/H₂O₂ processes result in the formation of OH radicals in solution,
49 which accelerate the oxidation degradation of the organic compounds in water. The
50 use of H₂O₂ has a main disadvantage of high cost, whereas the low oxidation rate is
51 the major draw back of semiconductors, such as TiO₂. The combined use of H₂O₂ and
52 semiconductors is a way of solving this problem. Many studies have been devoted to
53 the examination of organic compound photodegradation in the presence of H₂O₂ and
54 TiO₂ [5,6]. This process is usually called Fenton-like process because it is similar to
55 the advanced oxidation process based on the homogeneous Fenton reagent (Fe²⁺/H₂O₂)
56 or Fenton-like (Fe³⁺/H₂O₂) [7,8]. Up to now, various Fenton and Fenton-like
57 processes have been used for the degradation of organic pollution. For example,
58 activated carbon fibers [9], impure bismuth ferrite [10], copper slag (90% Fe₂SiO₄)
59 [11], ferrioxalate complexes [12], iron/ordered mesoporous carbon catalyst [13], iron
60 oxide nanotube layer [14], Cu²⁺ [15], et al. have been used as Fenton-type
61 photocatalyst or assisted Fenton-type photocatalysts. However, the photocatalytic and
62 Fenton-like photocatalytic activities of Ni_{1-x}Co_xFe₂O₄ ferrite nanoparticles have not
63 been reported as dye removal from waste water.

64 To date, many methods have been developed to synthesize spinel ferrite
65 nanoparticles, such as aerosol route [16], co-precipitation method [17, 18], ceramic
66 technique [19], hydrolysis method [20], microwave-hydrothermal method [21], and

hydrothermal method [22]. The hydrothermal process has been widely used to synthesize the spinel ferrites because of its simple process, low cost, low synthesis temperature and small particle size [22].

In this study, we focus on hydrothermal synthesis of $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles, examining the effect of Co content on microstructure, photocatalytic activity for malachite green removal from aqueous solution, and magnetic property of the nanoparticles.

74

75 **2. Experimental**

Nickel chloride ($\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$, Shenyang Hua Bai Tai Chemical Co. Ltd., China), cobalt chloride ($\text{CoCl}_2 \cdot 6\text{H}_2\text{O}$, Hebei Kingway Chemical Co. Ltd., China), and iron nitrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, Beijing Baishunchem. Co. Ltd., China) were used as starting materials. The starting materials were all analytical agent without further processing. The starting materials were first weighed according to the compositions of $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ ($x=0, 0.2, 0.4, 0.6, 0.8, \text{ and } 1.0$) and dissolved in 15 mL deionized water. The solutions have Fe^{3+} concentration of 0.02 mol L^{-1} . The solutions were then transferred into autoclaves (volume: 25 mL). Subsequently, NaOH with fourfold gram equivalent of all metal cations was dissolved in deionized water (5 mL) and added dropwise into the metal cation aqueous solutions with constant magnetic stirring. The use of excess NaOH can assure full precipitation of all cations. After sealing, hydrothermal reaction was carried out in a hydrothermal oven at 180°C for 24 h. Heating rate was about $30^\circ\text{C} \cdot \text{min}^{-1}$. After naturally cooling in the oven, the products were finally washed repeatedly with distilled water, and then dried at 100°C for 24

90 h.

91 Phase composition of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles was identified by using
 92 X-Ray diffractometer (XRD, $\text{CuK}_{\alpha 1}$, $\lambda=0.15406\text{nm}$, Model No: D/Max--2200PC,
 93 Rigaku, Japan). Morphology of the nanoparticles was analyzed by using scanning
 94 electron microscope (SEM, Model No: JXM-6700F, Japan). Fourier transform
 95 infrared spectra of the nanoparticles were measured with Fourier transform infrared
 96 spectrometer (FTIR, Model no: VERTEX 70, Bruke, German). KBr was used as
 97 matrix to disperse the ferrite nanoparticles for compressing disk sample. Absorbance
 98 spectra of the nanoparticles were determined with an ultraviolet-visible
 99 spectrophotometer (Model No: 722, Hengping, China). Magnetic property was
 100 measured with a vibrating sample magnetometer (VSM, Model No: Versa Lab,
 101 Quantun Design, USA)

102 To study the photocatalytic and photo-Fenton like degradation of malachite green in
 103 a water on the nanoparticles, malachite green aqueous solution with a concentration of
 104 $1 \times 10^{-6} \text{ M}$ was first prepared. In each experiment, 50 mL malachite green aqueous
 105 solution and 25 mg the ferrite nanoparticles were added into a glass beaker with
 106 constant stirring for 1-2 min. The photocatalysis experiment was carried out under the
 107 irradiation of sunlight. The intensity of sunlight reaching the surface of the solutions
 108 measured with a solar power meter (Model no: SM206, China) was $\sim 250 \text{ W} \cdot \text{m}^{-2}$.
 109 After leaving to steady state in dark for 10 min and at each irradiation interval, $\sim 3 \text{ mL}$
 110 solutions were took out and filtrated out the suspended tiny particles and subsequently
 111 measured to check their absorbance on a spectrophotometer (Model No: 722N,

112 Hengping, China). The solutions after the test were returned to the beakers to
113 maintain the normal volume of the solutions under test. Similar experiment was
114 carried out by adding 0.5 mL H₂O₂ into each of the 50 mL dye aqueous solution.

115 In first hour of the above processes, the oxidation-reduction potential (ORP) of the
116 malachite green aqueous solutions with and without the photocatalysts was determined
117 by using an oxidation-reduction potential tester (ORP-286, China). The ORPs of the
118 nanoparticle surfaces in the condition of dye photodegradation were estimated by
119 calculating the differences between the measured ORP of the dye aqueous solutions
120 with and without the nanoparticles. The absorbance and ORP of the dye aqueous
121 solutions were all the average value of two repeated measurement values

122

123 **3. Results and discussion**

124 **3.1. XRD analysis**

125 Figure 1a shows XRD patterns of the synthesized nanoparticles. All diffraction
126 peaks match with the diffraction data of spinel ferrites. This indicates that the
127 nanoparticles are single phase. The intensity of the XRD peaks first slightly decreases
128 when the Co content (x) is increased from 0 to 0.8 and then increases with further
129 cobalt substitution, drawing out variation trend in crystallinity of the nanoparticles.
130 This decrease trend of the crystallinity with cobalt substitution was also reported for
131 the Ni_{1-x}Co_xFe₂O₄ nanoparticles synthesized by using solvothermal route [23]. This
132 could be mainly due to smaller radius difference (0.72–0.64 Å) between Ni²⁺ and
133 Fe³⁺ ions than that (0.74–0.64 Å) between Co²⁺ and Fe³⁺ ions. The smaller radius

134 difference leads to smaller inhibition of Ni^{2+} substitution for Fe^{3+} to the spinel crystal
 135 growth than Co^{2+} substitution. Moreover, the position of strongest peak (311) shifts to
 136 lower 2θ with Co substitution (Fig. 1b). This can be ascribed to the increase in the
 137 interplanar crystal spacing (d) based on Bragg's equation. The lattice parameter of the
 138 nanoparticles with cubic crystal structure can be calculated by following equation
 139 with the XRD analysis data:

$$140 \quad \frac{a^2}{d^2} = h^2 + k^2 + l^2 \quad (1)$$

141 Calculated a values are 0.8236 nm, 0.8263 nm, 0.8298 nm, 0.8321 nm, 0.8339 nm
 142 and 0.8377 nm for the Co content $x=0, 0.2, 0.4, 0.6, 0.8,$ and 1.0 , respectively (Fig.
 143 1c). This indicates the expansion of the lattice with the cobalt substitution, agreeing
 144 with the shift of (311)-peak. Similar lattice parameter variation was also reported in
 145 previous literature [16, 24]. Moreover, the lattice parameter a of CoFe_2O_4 equals to
 146 0.8391 nm (JCPDS: 22-1086) that is larger than 0.83379 nm (JCPDS: 74-2081) and
 147 0.83390 nm (JCPDS: 10-0325) of the NiFe_2O_4 . Furthermore, the lattice parameter of
 148 the all ferrites is smaller than the value given in the JCPDS card, especially as the Co
 149 content approaches zero. This could be ascribed to the high-pressure effect in the
 150 condition of hydrothermal synthesis. Similarly, the lattice parameter of the NiFe_2O_4
 151 nanoparticle is smaller when they were synthesized by using hydrothermal process
 152 than sol-gel method [25]. The average crystal sizes of the nanoparticles are
 153 determined from XRD data with Debye–Scherrer's formula [26]:

$$154 \quad D = \frac{0.9\lambda}{\beta \cos \theta} \quad (2)$$

155 where λ is the X-ray wavelength, β the full width at half maximum (FWHM) of the

156 considered peak and θ is the Bragg angle. The results are 23.4, 29.4, 23.6, 19.4, 16.5,
157 and 14.8 nm for the $x=0, 0.2, 0.4, 0.6, 0.8, 1.0$, respectively.

158 **3.2. SEM**

159 Figure 2 shows SEM micrographs of the nanoparticles. Most of the nanoparticles
160 show spherical morphology with some agglomeration (Fig. 2c–2f), while the
161 $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ ($x=0.8$ and 1.0) nanoparticles have approximately cubical morphology
162 (Fig. 2a and 2b). This could be mainly due to same reason of the difference in
163 crystallinities of the nanoparticles. From the SEM micrographs, the average particle
164 sizes are also increased as increasing x from 0 to 0.8 and then decreased with further
165 cobalt substitution. The sizes of the nanoparticles with $x=0.8$ and 1.0 are obviously
166 larger than the results of XRD analysis, which means that these nanoparticles are
167 polycrystalline.

168 **3.3. FTIR analysis**

169 Figure 3 shows FTIR spectra of the nanoparticles. The peak centered at $\sim 3416\text{ cm}^{-1}$
170 is attributed to the stretching vibration of surface hydroxyls absorbed on surface and
171 O–H groups in absorbed water [27]. The peak centered at 1620 cm^{-1} is assigned to the
172 H–O–H bending vibration in water molecular [28] or the OH deformation vibration
173 due to surface hydroxyls [29, 30]. These imply good nanoparticle surface
174 hydrophilicity that may be favorable for the photocatalytic activity. The weak peak at
175 1124 cm^{-1} could be assigned to the C–O stretching [31] due to the adsorbed CO_2 . The
176 two peaks at $\sim 483\text{ cm}^{-1}$ and $\sim 616\text{ cm}^{-1}$ are assigned to the vibrations of ferrite groups
177 [32], corresponding to the octahedral and tetrahedral sites of positive ions in the

178 ferrite, respectively [28, 33]. The difference in absorption positions between the
179 octahedral and tetrahedral complexes of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ crystals is due to the
180 different distances between $\text{Fe}^{3+}-\text{O}^{2-}$ in the octahedral and tetrahedral sites. This
181 confirms the formation of single phase $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ structure.

182 **3.4. Optical absorption**

183 Figure 4 shows absorbance spectra of the ferrite nanoparticles. The absorbances in
184 UV-visible region are large and increase with increasing Co content. The estimated
185 absorption edge increases from ~648 nm to ~710 nm. Accordingly, the band gap
186 energies of the nanoparticles decrease from ~1.91 eV to ~1.75 eV (Inserted figure in
187 Fig. 4).

188 **3.5. Photocatalytic degradation of the dye in water**

189 Figure 5 shows concentration variations of the malachite green aqueous solutions on
190 the nanoparticles with the irradiation time of sunlight. The degradation rate increases
191 with increasing Co content. This increase of degradation rate could be ascribed to the
192 decrease of band gap and average particle size and the increase of light absorbance of
193 nanoparticles as the increase of Co content. In addition, the ORP values are negative
194 and decrease (Fig. 6). This indicates that the nanoparticles surface are dominantly
195 reductive in the photocatalysis condition, This characteristics is enhances with
196 increasing Co content.

197 **3.6. Fenton-like photodegradation**

198 Figure 7 shows concentration variations of the malachite green aqueous solution
199 with H_2O_2 on the nanoparticles with the irradiation time of sunlight. The degradation

is obviously faster than that without H₂O₂, which indicates a significant photo-Fenton-like reaction. Similarly, the degradation rate increases as the Co content is increased. This increase could also be ascribed to the decrease of band gap and average particle size and the increase of light absorbance. The photo-generated electron-hole pairs in the nanoparticles could play similar role of Fe²⁺ and Fe³⁺ in Fenton reaction. The concentration increase in photo-generated electrons and holes leads to the enhanced photo-Fenton-like reaction. The ORP values in this process are larger than those in the cases without H₂O₂. The ORP also shows a nonlinear variation with Co contents, (Fig. 6). The difference and variation of ORP could be related to the surface characteristics of the nanoparticles, the acidic-alkaline behavior of the dye, oxidation of H₂O₂ and Fenton-like reaction.

Kinetic relation between concentration (*C*) of the malachite green aqueous solution and photocatalytic reaction time (*t*) can be given by:

$$\frac{C_0}{C} = A \exp\left(\frac{kt}{T}\right) \quad (3)$$

where *C*₀ is initial concentration, *k* is quasi-kinetic rate constant, *T* is reaction temperature and *A* is a constant. Fig. 8 shows the plots of ln(*C*/*C*₀) versus *t*. The plots are approximately linear. The *k* values can be estimated directly from the plots. The estimated *k* values are in the range of 2.23–7.2×10⁻² min⁻¹, which is increased nearly one order of magnitude to 1.3–6.0×10⁻¹ min⁻¹ as H₂O₂ is used. The *k* values increase with increasing Co content in both cases with and without H₂O₂.

3.7. Magnetic property of the nanoparticles

Figure 9a show room temperature hysteresis loops of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles. The nanoparticles are all ferrimagnetic. With increasing applied field, the magnetization of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles increases, and reaches saturation state under highest applied magnetic fields of 30 kOe. Maximum value of magnetization at applied field of 30 KOe (saturation magnetization M_s) is in the ranges of 50.7–64.2 $\text{emu}\cdot\text{g}^{-1}$ (Fig. 9b). The coercivity (H_c) is in the range of 0.4–1.7 kOe (Fig. 9b). The ferrite nanoparticles with Co content $x=0.8$ show maximal M_s and H_c . This can be mainly ascribed to the maximal cation distribution of Fe^{3+} and Co^{2+} at the octahedral site (B-site) since the magnetic moments of Zn^{2+} , Co^{2+} and Fe^{3+} are 0 μ_B , 3 μ_B and 5 μ_B , respectively. Other reasons include the difference in particle size, easy magnetization axis and shape anisotropy. The large M_s and low H_c can provide excellent magnetic separation performance for the ferrite nanoparticles in the final degraded dye aqueous solution.

234

235 4. Conclusions

Single phase $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ ($x=0.1-1.0$) ferrite nanoparticles showed high photocatalytic activity in the sunlight-excited photodegradation of malachite green in water. The addition of small amount of H_2O_2 resulted in remarkably enhanced photodegradation, indicating the present of Fenton-like reaction. Due to the increases in light absorbance and the decrease in band gap and average particle size, the photodegradation and Fenton-like photodegradation rates increased with increasing Co content. The ferrite nanoparticles also showed high saturation magnetizations and

low coercivities, which ensured that they can be easily separated after the photodegradation.

Acknowledgements: The authors thank the Mr. H. Tian of the Northwest Institute for Non-Ferrous Metal Research for his kind assistance in SEM measurement

References

- [1] P.-G. Guo, G.-L. Zhang, J.-Q. Yu, H.-L. Li, X.-S. Zhao, Controlled synthesis, magnetic and photocatalytic properties of hollow spheres and colloidal nanocrystal clusters of manganese ferrite, *Colloids and Surf., A* 395 (2012) 168-174
- [2] E. Casbeer, V.K. Sharma, X.-Z. Li, Synthesis and photocatalytic activity of ferrites under visible light: A review, *Sep. Purif. Technol.* 87 (5) (2012) 1-14
- [3] A.A. Aziz, K.S. Yong, S. Ibrahim, S. Pichiah, Enhanced magnetic separation and photocatalytic activity of nitrogen doped titania photocatalyst supported on strontium ferrite, *J. Hazard. Mater.* 199–200 (15) (2012) 143–150
- [4] Y.-S. Fu, H.-Q. Chen, X.-Q. Sun, X. Wang. Combination of cobalt ferrite and graphene: High-performance and recyclable visible-light photocatalysis, *Appl. Catal. B: Environ.* 111–112 (12) (2012) 280-287
- [5] Adrián M.T. Silva, Ekaterini Nouli, Nikolaos P. Xekoukoulotakis and Dionissios Mantzavinos, Effect of key operating parameters on phenols degradation during H₂O₂-assisted TiO₂ photocatalytic treatment of simulated and actual olive mill wastewaters, *Appl. Catal. B: Environ.* 73(1–2)(2007) 11–22

- 266 [6] Emad S. Elmolla, and Malay Chaudhuri, Photocatalytic degradation of amoxicillin,
267 ampicillin and cloxacillin antibiotics in aqueous solution using UV/TiO₂ and
268 UV/H₂O₂/TiO₂ photocatalysis, *Desalination* 252(1–3) (2010) 46–52
- 269 [7] Neamtu M, Zaharia C, Catrinescu C, Yediler A, Macoveanu M, Kettrup I A,
270 Fe-exchanged Y zeolite as catalyst for wet peroxide oxidation of reactive azo dye
271 Procion Marine H-EXL, *Appl Catal B: Environ.* 48 (2004) 287–294.
- 272 [8] Guelou E, Barrault J, Fournier J, Tatibouet JM, Active iron species in the catalytic
273 wet peroxide oxidation of phenol over pillared clays containing iron, *Appl Catal*
274 *B: Environ.* 44 (2003) 1–8.
- 275 [9] Lie Wang, Yuyuan Yao, Zhanhao Zhang, Lijie Sun, Wangyang Lu, Wenxing Chen,
276 Haixiang Chen, Activated carbon fibers as an excellent partner of Fenton catalyst
277 for dyes decolorization by combination of adsorption and oxidation, *Chem. Eng. J.*
278 251 (2014) 348–354
- 279 [10] Tayyebi Soltani, Mohammad H. Entezari, Solar-Fenton catalytic degradation of
280 phenolic compounds by impure bismuth ferrite nanoparticles synthesized via
281 ultrasound, *Chem. Eng. J.* 251 (2014) 207–216
- 282 [11] M. Solís-López, A. Durán-Moreno, F. Rigas, A.A. Morales, M. Navarrete, R.M.
283 Ramírez-Zamora, Assessment of copper slag as a sustainable Fenton-type photo-
284 catalyst for water disinfection, *Water Reclamation and Sustainability* June (2014)
285 199–227
- 286 [12] Isabelli N. Dias, Bruno S. Souza, João H.O.S. Pereira, Francisca C. Moreira,
287 Márcia Dezotti, Rui A.R. Boaventura, Vítor J.P. Vilar, Enhancement of the

photo-Fenton reaction at near neutral pH through the use of ferrioxalate
 complexes: A case study on trimethoprim and sulfamethoxazole antibiotics
 removal from aqueous solutions, *Chem. Eng. J.* 247 (2014) 302–313

[13] Feng Duan, Yuezhu Yang, Yuping Li, Hongbin Cao, Yi Wang, Yi Zhang,
 Heterogeneous Fenton-like degradation of 4-chlorophenol using iron/ordered
 mesoporous carbon catalyst, *J. Environ. Sci.* 26 (5) (2014) 1171–1179

[14] Jun-Won Jang, Jae-Woo Park, Iron oxide nanotube layer fabricated with
 electrostatic anodization for heterogeneous Fenton like reaction, *J. Hazard. Mater.*
 273 (30) (2014) 1–6

[15] Hye-Jin Lee, Hongshin Lee, Changha Lee, Degradation of diclofenac and
 carbamazepine by the copper(II)-catalyzed dark and photo-assisted Fenton-like
 systems, *Chem. Eng. J.* 245 (2014) 258–264

[16] T.E. Agustina, H.M. Ang, V.K. Vareek. A review of synergistic effect of photo-
 catalysis and ozonation on wastewater treatment, *J. Photochem. Photobiol. C:*
Photochem. Rev. 6 (2005) 264–273

[17] V.L. Mathe, A.D. Sheikh. Magnetostrictive properties of nanocrystalline Co–Ni
 ferrites, *Physica B* 405 (2010) 3594–3598

[18] R. Arulmurugan, G. Vaidyanathan, S. Sendhilnathan, B. Jeyadevan, Thermo-
 magnetic properties of $\text{Co}_{1-x}\text{Zn}_x\text{Fe}_2\text{O}_4$ ($x=0.1-0.5$) nanoparticles, *J. Magn. Magn.*
Mater. 303 (2006) 131–137.

[19] A. Tawfik, I.M. Hamada, O.M. Hemeda, Effect of laser irradiation on the
 structure and electromechanical properties of Co–Zn ferrite, *J. Magn. Magn.*

- 310 Mater. 250 (2002) 77–82.
- 311 [20] G.V. Duong, N. Hanh, D.V. Linh, R. Groessinger, P. Weinberger, E. Schafner, M.
 312 Zehetbauer, Monodispersed nanocrystalline $\text{Co}_{1-x}\text{Zn}_x\text{Fe}_2\text{O}_4$ particles by forced
 313 hydrolysis: Synthesis and characterization, J. Magn. Magn. Mater. 311 (2007)
 314 46–50.
- 315 [21] C.-K. Kim, J.-H. Lee, S. Katoh, R. Murakami, M. Yoshimura, Synthesis of Co-,
 316 Co-Zn and Ni-Zn ferrite powders by the microwave-hydrothermal method, Mater.
 317 Res. Bull. 36 (2001) 2241–2250.
- 318 [22] F. Gözüak, Y. Köseoğlu, A. Baykal, H. Kavas, Synthesis and characterization of
 319 $\text{Co}_x\text{Zn}_{1-x}\text{Fe}_2\text{O}_4$ magnetic nanoparticles via a PEG-assisted route, J. Magn. Magn.
 320 Mater. 321 (2009) 2170–2177.
- 321 [23] Y. Tang, X.-W. Wang, Q.-H. Zhang, Y.-Q. Li, H.-Z. Wang, Solvothermal
 322 synthesis of $\text{Co}_{1-x}\text{Ni}_x\text{Fe}_2\text{O}_4$ nanoparticles and its application in ammonia vapors
 323 detection, Progress in Natural Science: Materials International 22 (2012) 53–58
- 324 [24] R. Mukherjee, T. Sahu, S. Sen, P. Sahu, Structural and microstructural evolution
 325 due to increasing Co substitution in $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$: An X-ray diffraction study
 326 using the Rietveld method, Mater. Chem. Phys. 128 (2011) 365–370
- 327 [25] M. Srivastava, S. Chaubey, A.K. Ojha, Investigation on size dependent structural
 328 and magnetic behavior of nickel ferrite nanoparticles prepared by sol–gel and
 329 hydrothermal methods, Mater. Chem. Phys. 118 (2009) 174–180

- 330 [26] H.P. Klug, L.E. Alexander, X-ray Diffraction Procedures for Polycrystalline and
331 Amorphous Materials, 2nd ed., John Wiley & Sons, New York, 1974.
- 332 [27] S. Yáñez-Vilar, M. Sánchez-Andújar, C. Gómez-Aguirre, J. Mira, M.A.
333 Señarís-Rodríguez, S. Castro-García, A simple solvothermal synthesis of MFe_2O_4
334 ($M^{1/4}Mn$, Co and Ni) nanoparticles, J. Solid State Chem. 182 (2009) 2685–2690.
- 335 [28] C.-H. Lu, S.-J. Liou, Hydrothermal preparation of nanometer lithium nickel
336 vanadium oxide powder at low temperature, Mater. Sci. Eng., B 75 (2000) 38–
337 42.
- 338 [29] P. Priyadharsini, A. Pradeep, P. Sambasiva Rao, G. Chandrasekaran, Structural,
339 spectroscopic and magnetic study of nanocrystalline Ni–Zn ferrites, Mater.
340 Chem. Phys. 116 (2009) 207–213
- 341 [30] X.-C. Shen, X.-Z. Fang, Y.-H. Zhou, H. Liang, Synthesis and characterization of
342 3-aminopropyltriethoxysilane-modified superparamagnetic magnetite nano-
343 particles, Chem. Lett. 33 (2004) 1468–1469.
- 344 [31] M. Ma, Y. Zhang, W. Yu, H.-Y. Shen, H.-Q. Zhang, N. Gu, Preparation and
345 characterization of magnetite nanoparticles coated by amino silane, Colloids Surf.
346 A 212 (2003) 219–226.
- 347 [32] H. Sozeri, Z. Durmus, A. Baykal, Structural and magnetic properties of
348 triethylene glycol stabilized $Zn_xCo_{1-x}Fe_2O_4$ nanoparticles. Mater. Res. Bull. 47
349 (2012) 2442–2448
- 350 [33] S.-H. Xiao, W.-F. Jiang, L.-Y. Li, X.-J. Li, Low-temperature auto-combustion

351 synthesis and magnetic properties of cobalt ferrite nanopowder, Mater. Chem.

352 Phys. 106 (2007) 82–87.

353

354

355

356

357

358

359

360

361

362

363

364

365

366

367

368

369

370 **Figures:**




Figure 1. (a) XRD patterns and (b) enlarged (311) peak. (c) Average particle size and lattice parameter of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles.






Figure 2. SEM micrographs of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles with various Co contents: (a) $x=0$, (b) $x=0.2$, (c) $x=0.4$, (d) $x=0.6$, (e) $x=0.8$ and (f) $x=1.0$.



388

389 Figure 3. FTIR spectra of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles.



390

391 Figure 4. Absorbance spectra of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles. The inset is the plot
392 of band gap (E_g) vs. Co content (x).


393

394

395

396


397



398

399 Figure 5. Concentration variations of malachite green aqueous solutions on the
400 $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles with the irradiation time of sunlight.

401




402

403 Figure 6. ORP variations of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles with Co content (x) in
404 the photocatalytic and photo-Fenton-like degradation systems.

405

406


407



408

409 Figure 7. Concentration variations of malachite green aqueous solutions containing
 410 H_2O_2 (concentration equals to 10 ml/l) on the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$ nanoparticles
 411 with irradiation time of sunlight.

412



413

414 Figure 8. Plots of $\ln(C/C_0)$ vs. irradiation time of sunlight without (a) and with (b)


415

H_2O_2 .

416

417

418



419

420 Figure 9. (a) Room temperature magnetic hysteresis loops of the $\text{Ni}_{1-x}\text{Co}_x\text{Fe}_2\text{O}_4$

421 nanoparticles and (b) variations of saturation magnetization and coercivity

422 as a function of Co content.

423

424