

Original Research Article

Improving the Slow Release System Using Chitosan-Alginate Nanoparticles with Various Methods for Curcumin

ABSTRACT

Biodegradable polymeric materials have been used as a drug delivery system due to its encapsulation, release system and less toxic properties. Chitosan-alginate nanoparticles were prepared by ionotropic pre-gelation of alginate core, followed by polyelectrolyte complexation of chitosan and curcumin was chosen as a model drug.

Aims: The aim of this study was to evaluate the possibility of chitosan-alginate nanoparticles as carriers for curcumin using various methods.

Study design: Lab. Experience

Place and Duration of Study: Department of Chemistry (LPPT and Analytical Laboratory), Universitas Gadjah Mada, Special Region of Yogyakarta, between September 2013 and May 2014.

Methodology: This preparation was divided into 4 methods to produce Alginate-Calcium-Chitosan (ACaK), Alginate-Chitosan-Calcium (AKCa), Chitosan-Alginate-Calcium (KACa) and Alginate-Chitosan (AK) nanoparticles. The amount of drug entrapped was determined by shaking the solution and then supernatant was analyzed for drug loading by measuring the absorbance, morphology, particle sizes and kinetics.

Results: The encapsulation efficiency was up to 85% in higher drug-polymer ratio and the effect of egg-box model made diameter of nanoparticles between 51 and 90 nm. The kinetic model of desorption for Alginate-Calcium-Chitosan, Alginate-Chitosan-Calcium and Chitosan-Alginate-Calcium nanoparticles followed Korsmeyer-Peppas.

Conclusion: This study suggest that these materials serve as suitable for uptake in capillary due to their nano-sized range and could stay long time into bloodstream.

Keywords: curcumin, release system, drug delivery, nanoparticles, kinetic

1. INTRODUCTION




Fig. 1. Chemical structure of curcumin.

Curcumin or (Diferuloylmethane) is a polyphenol derived from the herb *Curcuma longa* and commonly known as turmeric [1](Fig. 1). Curcumin has anti-carcinogenic [2-5], anti-HIV [6], anti-inflammatory [7-

12], antioxidant [13-15] and antitumor properties [16]. Despite extensive research and development, the properties of curcumin in aqueous solution were low bioavailability and poor solubility [17]. Therefore, curcumin is often limited by its potential to reach the site of therapeutic action. Curcumin has been reported that it is complex with cyclodextrin [18] and phospholipids [19] or encapsulated in solid lipid microparticles such as chitosan [20] and albumin [21]. A drug delivery system has opened up new possibilities in targeted and sustained release of drugs by nanotechnology [22]. A drug delivery system was designed by tiny nanoparticles and it can reach less accessible sites in the body. Controlled release of the drug from the nanoformulations could maintain steadier levels of drug in bloodstream for longer durations. Sustained release of drug can be achieved by encapsulation the active ingredient in a polymer matrix.

Chitosan (K) and sodium alginate (A) are extensively used in encapsulation of drug for the purpose of the sustained release [23]. Sodium alginate is an anionic polysaccharide obtained from marine algae and it is a water-soluble natural copolymer composed of guluronic and mannuronic acid units. In addition, chitosan is deacetylate derivatives of chitin, composed by β -(1, 4)-2-amino-2-deoxy-D-glucopyranose units and small amount of N-acetyl-D-glucosamine residues [24]. These are polysaccharide polymers, formed from repeating units (either mono- or di- saccharides) joined together by glycosidic bond [25]. They have many properties of an ideal carrier for drug delivery such as biocompatibility, biodegradability, low cost and non-toxicity [26]. Encapsulation of hydrophobic drugs into an aqueous nanoparticulate system has been attempted so as to deliver such drugs with their full potential [27]. Rajaonarivony et al. reported that poly-L-lysine/alginate nanoparticles were produced using a pre-gel method [28].

The objective of this study was to evaluate the possibility of chitosan-alginate nanoparticles as carriers for curcumin. The challenge was to entrap hydrophobic molecules such as curcumin into hydrophilic nanoparticles formed by ionotropic pre-gelation of the alginate core followed by chitosan polyelectrolyte complexation. The final samples were characterized using Fourier Transform Infrared spectrometer (FTIR), Scanning Electron Microscope (SEM) and Transmission Electron Microscope (TEM), respectively. In addition, curcumin release was analyzed using Ultraviolet-Visible (UV-Vis). The release properties of nanoparticles in ratio of phosphate buffered saline and ethanol (80:20) at pH 7.4 were also studied.

2. MATERIAL AND METHODS / EXPERIMENTAL DETAILS / METHODOLOGY

2.1 Preparation of Curcumin Loaded Chitosan-Alginate Nanoparticles

Sodium alginate and calcium chloride solutions were prepared by dissolving the chemicals in distilled water. However, chitosan was dissolved in 1 % acetic acid solution and curcumin was dissolved in ethanol. The pH of the sodium alginate and chitosan solution was adjusted to 5 using hydrochloric acid and sodium hydroxide, respectively.

This preparation was divided into 4 methods to produce Alginate-Calcium-Chitosan (ACaK), Alginate-Chitosan-Calcium (AKCa), Chitosan-Alginate-Calcium (KACa) and Alginate-Chitosan (AK) nanoparticles. Calcium chloride solution 18 mM (2.5 mL) was added dropwise to 25 mL aqueous sodium alginate 0.12% (w/v) while stirring for 30 minutes. Two mL of curcumin solution 1% (w/v) and 10 mL chitosan solution 0.05% (w/v) were added into the resultant calcium alginate pre-gel and stirred for an hour called as ACaK. AKCa were obtained as ACaK, but calcium chloride solution was added after mixing alginate and chitosan solution. KACa were obtained as AKCa, but 10 mL alginate solution was added into 25 mL of chitosan solution. Chitosan solution (10mL) and 23 mL distilled water were added into 25 mL alginate solution and stirred for an hour called as AK.

The resultant suspensions were equilibrated overnight at room temperature to allow nanoparticles and to form uniform particle sizes and then separated by centrifugation at 4 °C. Particles were dried using a freeze dryer overnight. Blank nanoparticles were obtained as a previous procedure of curcumin loaded nanoparticles, but they were not added by curcumin solution. They were called as AK-0, ACaK-0, AKCa-0 and KACa-0.

The amount of drug entrapped was determined by shaking the solution and then supernatant was analyzed for drug loading by measuring the absorbance at 426 nm in UV spectrophotometer. The

73 confirmation of drug loading was done by comparing optical absorbance of nanoformulations with and
74 without drug loading.

75 $\% \text{ encapsulation} = (\text{drug input (mg)} - \text{drug in supernatant (mg)}) / (\text{drug input (mg)}) \times 100\%$

76
77 The morphology, measurements of particle sizes and functional groups of the nanoparticles were
78 performed using Scanning Electron Microscope (SEM) (JEOL, JSM-6510), Transmission Electron
79 Microscope (TEM) (JEOL, JEM-1400) and Fourier Transform Infrared spectra (FTIR), respectively.
80 Sample preparation using FTIR was taken with KBr pellets on a FTIR spectrometer (Shimadzu-
81 Prestige 21).

82

83 2.2 In Vitro Release of Curcumin

84 To establish the curcumin release profiles from nanoparticles, the curcumin loaded nanoparticles
85 were separated from matrix by shaking at 37°C in various times. At appropriate intervals, five mL
86 solution was taken and analyzed using UV spectrophotometer. The mathematical models such as
87 zero-order, first-order, Higuchi, and Korsmeyer-Peppas equations were fitted to individual dissolution
88 data.

89 Zero-order model is used to describe the drug solution of modified release drug slowly. It can be
90 represented by the question: $Q_0 - Q_t = K_0 \cdot t$, where K_0 is the zero order release constant expressed in
91 units of concentration/time, Q_0 is the initial amount of drug in the solution and Q_t is the amount of
92 drug dissolved in time t . Data obtained from in vitro drug release studies were plotted as cumulative
93 amount of drug release vs time [29].

94 First order model has also been used to describe absorption and/or elimination of some typical drugs.
95 This release model can be expressed by the equation: $dC/dt = -Kc$, where K is the first order rate
96 constant expressed in units of time⁻¹, t is the time and C is concentration of drug. The data obtained
97 were plotted as log cumulative percentage of drug remaining vs time which would yield a straight line
98 with a slope of $(-K)/2.303$ [30].

99 Higuchi model is to describe drug release from a matrix system and based on hypotheses that (i)
100 initial drug concentration in the matrix is much higher than drug solubility; (ii) drug diffusion takes
101 place only in one dimension (edge effect must be negligible); (iii) drug particles are much smaller than
102 system thickness; (iv) matrix swelling and dissolution are negligible; (v) drug diffusivity is constant;
103 and (vi) perfect sink conditions are always attained in the release environment. To express model is
104 given by the equation: $ft = Q = A \sqrt{D(2C - C_s) C_s \cdot t}$, where C is the drug initial concentration, C_s is the
105 drug solubility in the matrix media, D is the diffusion coefficient in the matrix substance, ft or Q is the
106 amount of drug released in time (t) per unit area (A) and t is time. In addition, the model is possible to
107 simplify the Higuchi model as $ft = Q = KH \cdot t^{1/2}$ [31], where KH is the Higuchi dissolution constant [32].
108 The data obtained were plotted as cumulative percentage drug release vs square root of time [33].

109 Korsmeyer-Peppas model has been used to describe drug release from a polymeric system equation.
110 This equation can be expressed as $M_t / M_\infty = K \cdot t^n$, where k is the release rate constant, M_t / M_∞ is a
111 fraction of drug released at time (t) and n is the release exponent. The n value is used to characterize
112 different release for cylindrical shaped matrices [34]. In this case of cylindrical tablet, $0.45 \leq n$
113 corresponds to a Fickian diffusion mechanism, $0.45 < n < 0.89$ to non-Fickian transport, $n = 0.89$ to
114 case II transport (relaxation), and $n > 0.89$ to super case II transport [35]. To study the release
115 kinetics, data obtained from in vitro drug release studies were plotted as log cumulative percentage
116 drug release vs log time. To find out the mechanism of drug release, the first 60% drug release data
117 should be used.

118 3. RESULTS AND DISCUSSION

119 3.1 Preparation of Chitosan-Alginate Nanoparticles

120 Chitosan-alginate nanoparticles were obtained by spontaneously under very mild conditions.
121 Preparation of chitosan-alginate nanoparticles appeared some typical peaks. IR spectra of chitosan
122 (Fig. 2(a)) showed the broad band at 3448 cm^{-1} corresponded to the amine and hydroxyl groups. The
123 absorption bands of carbonyl stretching of the secondary amide (amide I band) and the bending
124 vibrations of the N-H (amide II band) were at 1651 cm^{-1} and 1597 cm^{-1} , respectively. The peak of
125 secondary hydroxyl group observed was at 1087 cm^{-1} . The band in the IR spectra of sodium alginate

(Fig. 2(b)) at 1419 cm^{-1} and 1612 cm^{-1} was assigned to symmetric and asymmetric stretching peaks of carboxylate salt groups. In addition, the absorption band of alginate at 1612 cm^{-1} shifted to 1627 cm^{-1} after reacting with chitosan (Fig. 2(c)) as polyelectrolyte complexation. The AK-0 was used to control between other samples added by calcium ions (Ca). FTIR spectra of sodium alginate and calcium ions appeared a specific peak at 1080 cm^{-1} indicating hydroxyl groups interacted with calcium ions. The peaks of ACaK-0 and KACa-0 were observed at 1620 cm^{-1} and 1604 cm^{-1} , respectively (Fig. 2(d and e)). They indicate that calcium ions interacted with carboxylate ions of sodium alginate to form an egg-box model. The IR spectra of AKCa-0 (not shown) had identical peaks with ACaK-0.





Fig. 2. FTIR spectra of chitosan (a), sodium alginate (b), AK-0 (c), ACaK-0 (d) and KACa-0 (e).

The FTIR was adopted to characterize the potential interaction between 2 polymers and calcium ions into nanoparticles. As shown in Fig. 3 (a), IR spectra of curcumin had specific peaks at 1427 cm^{-1} and 1512 cm^{-1} as aromatic rings, Carbon double bond was at 1627 cm^{-1} , methoxy stretching peak appeared at 2854 cm^{-1} and a broad band at 3510 cm^{-1} was attributed to the stretching vibration of the OH groups. IR spectra of AK that observed the asymmetrical stretching of carboxyl groups at 1627 cm^{-1} shifted to 1635 cm^{-1} (Fig. 3 (b and c)), which probably indicates that curcumin molecule was filled in the polymeric network. In addition, these results indicate that carboxylate groups of alginate associate with ammonium groups of chitosan through electrostatic interactions to form the polyelectrolyte complexation. The IR spectra of ACaK-0 and ACaK at 1620 cm^{-1} shifted to 1627 cm^{-1} and 3425 cm^{-1} to 3433 cm^{-1} (Fig. 3 (d and e)). In addition, IR spectra of KACa-0 and KACa at 1604

147 cm^{-1} shifted to 1627 cm^{-1} and 3441 cm^{-1} shifted to 3433 cm^{-1} (Fig.3 (f and g)).



148

149 **Fig. 3. FTIR spectra of curcumin (a), AK-0 (b), AK (c), ACaK-0 (d), ACaK (e), KACa-0 (f) and**
150 **KACa (g).**

151 An analysis of electron microscopy was confirmed the presence of nanoparticles and provided
152 morphological information of the typical curcumin loaded chitosan-alginate nanoparticles using the
153 transmission electron microscope (TEM) and scanning electron microscope (SEM), respectively. Fig.
154 4 showed the comparison of 2 methods between ACaK and AKCa because calcium ion had unique
155 characteristics to design small particles. Particle sizes were about between 51 and 90 nm depending
156 on methods and particles were seen to be spherical solid. The interaction between alginate and
157 calcium ions produced egg-box model and the diameters were smaller than without producing egg-
158 box model because calcium-alginate complex in pre-gel state was enveloped by chitosan as cationic
159 polymer. Fig. 5 showed appearances in the form of dry solids between with and without calcium ions.
160 If they were dispersed, they would be able to decompose easily into nanometer sizes. Encapsulation
161 efficiencies of ACaK, AKCa and KACa were 85.38, 65.00 and 73.22%, respectively (Fig. 6). The result
162 shows calcium ions interacted between alginate and chitosan because the matrix produced egg-box
163 model and nano-sized particles. Therefore, these nanoparticles are effective to entrap curcumin as a
164 drug model.




Fig. 4. TEM Images of curcumin loaded nanoparticles, ACaK (a), AKCa (b).




Fig. 5. SEM Images of nanoparticles without (a) and with calcium ions (b).




Fig. 6. Encapsulation efficiency of ACaK, AKCa and KACa nanoparticles.

3.2 In Vitro Release of Curcumin

The release of ACaK has been reached the slowest because ACaK produced egg-box models that have an ability to control curcumin release from matrix slowly, but AKCa has the fast curcumin release because they could not produce egg-box models well and the effect is that only little curcumin entrapped into matrix between alginate and chitosan. In many experimental situations, including the case of drug release from swellable polymeric systems, the mechanism of drug release diffusion deviates from the Fickian equation and follows a non-Fickian behavior (anomalous). In the cases, the following general equation or its logarithmic form can be used as cylindrical tablets, values of n between 0.45 and 0.89 indicate both diffusion and swelling controlled drug release (anomalous transport). Values above 0.89 indicate case-II transport which related to polymer relaxation during hydrogel swelling and values below 0.45 indicate that drug release from polymer is due to Fickian diffusion.

The n and k values were obtained from releasing curve (Fig. 7) and presented in Table 1. The n value is the diffusional exponent that can be related to the drug transport mechanism. The ACaK, AKCa and KACa fitted to Korsmeyer-Peppas' model. The values of n for ACaK, AKCa and KACa were 0.591, 0.333 and 0.283, respectively. The ACaK mechanism followed diffusion and erosion, but both AKCa and KACa mechanisms only followed diffusion. Therefore, ACaK was very effective to be a drug release system because a drug model could release slower than others and then the matrix will be broken by erosion after releasing curcumin slowly. In addition, the ACaK produced egg-box models easily because calcium ions were interacted into carboxylic groups of alginate well, but the first interactions between alginate and chitosan of AKCa and KACa did not produce egg-box models because carboxylate of alginate have interacted with amine of chitosan to form polyelectrolyte complex. Therefore, calcium ions did not have ability to interact into functional group of alginate and ethanol was added into phosphate buffered saline to increase the solubility of curcumin, then the kinetic model could be reached gap clearly than others.




Fig. 7. In vitro curcumin release (%) from ACaK, AKCa and KACa in mixing PBS and ethanol solution at 37°C

Table 1. Estimated parameters and drug release mechanisms of curcumin loaded chitosan-alginate nanoparticles

Nanoparticle	Kinetic Model	Kinetic constant (k)	r ²	Diffusional exponent (n)
ACaK	Zero Order	0.198	0.928	0.591
	First Order	0.010	0.976	
	Higuchi	5.266	0.984	
	Korsmeyer-Peppas	3.327	0.995	
AKCa	Zero Order	0.048	0.698	0.333
	First Order	0.001	0.722	
	Higuchi	1.341	0.838	
	Korsmeyer-Peppas	7.091	0.968	
KACa	Zero Order	0.133	0.818	0.283
	First Order	0.013	0.937	
	Higuchi	3.606	0.918	
	Korsmeyer-Peppas	19.191	0.977	

4. CONCLUSION

In this study, the possibility to entrap hydrophobic curcumin was successfully compounded within chitosan-alginate nanoparticles using a very simple ionotropic pre-gelation and polyelectrolyte complex techniques. The diameters of nanoparticles were obtained between 51 and 90 nm. The encapsulation efficiency was up to 85% in higher drug-polymer ratio. The kinetic model of desorption for ACaK, AKCa and KACa nanoparticles followed Korsmeyer-Peppas. These materials are suitable for uptake in capillary due to their nano-sized range and could stay long time into bloodstream.

REFERENCES

1. Anderson AM, Mitchell MS, Mohan RS. Isolation of curcumin from turmeric. J. Chem. Educ. 2000;77:359–360.
2. Aggarwal BB, Kumar A, Bharti AC. Anticancer potential of curcumin: preclinical and clinical studies. Anticancer Res. 2003;23:363-398.
3. Rao CV, Rivenson A, Simi B, Reddy BS. Chemoprevention of colon carcinogenesis by dietary curcumin, a naturally occurring plant phenolic compound. Cancer Res. 1995;55:259-266.
4. De R, Kundu P, Swarnakar S, Ramamurthy T, Chowdhury A, Nair GB, Mukhopadhyay A K. Antimicrobial activity of curcumin against helicobacter pylori isolates from India and during infections in mice. Antimicrob. Agents Chemother. 2009;53:1592–1597.
5. Wang Y, Lu Z, Wu H, Lv F. Study on the antibiotic activity of microcapsule curcumin against foodborne pathogens. Int. J. Food Microbiol. 2009;136: 71–74.
6. Jordan WC, Drew CR. Curcumin: a natural herb with anti-HIV activity. J. Natl. Med. Assoc. 1996;88:333–334.
7. Lantz RC, Chen GJ, Solyom AM, Jolad SD, Timmermann BN. The effect of turmeric extracts on inflammatory mediator production. Phytomedicine. 2005;12:445-452.
8. Ammon HP, Wahl MA. Pharmacology of curcuma longa. Planta Med. 1991;57:1-7.
9. Brouet I, Ohshima H. Curcumin, an anti-tumor promoter and anti-inflammatory agent, inhibits induction of nitric oxide synthase in activated macrophages. Biochem. Biophys. Res. Commun. 206 (1995) 533-540.
10. Dikhsit M, Rastologi L, Shukla R, Srimal RC. Prevention of ischaemia-induced biochemical changes by curcumin and quinidine in the cat heart. Ind. J. Med. Res. 1995;101:31-50.
11. Srimal RC, Dhawan BN. Pharmacology of diferyloyl methane (curcumin), a non-steroidal anti-inflammatory agent. J. Pharm. Pharmacol. 1973;25:447–452.
12. Aggarwal BB, Harikumar KB. Potential therapeutic effects of curcumin: the anti-inflammatory agent against neurodegenerative cardiovascular, pulmonary, metabolic, autoimmune and neoplastic diseases. Int. J. Biochem. Cell Biol. 2009;41:40–59.
13. Ruby AJ, Kuttan G, Babu KD, Rajasekharan KN, Kuttan R. Antitumor and antioxidant activity of natural curcuminoids. Cancer Lett. 1995;94:79-83.

14. Pizzo P, Scapin C, Vitadello M, Florean C, Gorza, L. Grp 94 acts as a mediator of curcumin-induced antioxidant defence in myogenic cells. *J. Cell. Mol. Med.* 2010;14:970–981.
15. Sugiyama Y, Kawakishi S, Osawa T. Involvement of the diketone moiety in the antioxidative mechanism of tetrahydrocurcumin. *Biochem. Pharmacol.* 1996;52:519–525.
16. Lee YK, Lee WS, Hwang JT, Kwon DY, Surh YJ, Park OJ. Curcumin exerts anti-differentiation effect through AMPKR-PPARin 3T3-L1 adipocytes and anti-proliferatory effect through AMPKRCOX-2 in cancer cells. *J. Agric. Food Chem.* 2009;57:305–310.
17. Anand P, Kunnumakkara AB, Newman RA, Aggarwal BB. Bioavailability of curcumin: problems and promises. *Mol. Pharm.* 2007;4:807-818.
18. Yallapu MM, Jaggi M, Chauhan SC. Poly (β -cyclodextrin)/curcumin self-assembly: a novel approach to improve curcumin delivery and its therapeutic efficacy in prostate cancer cells. *Macromol. Biosci.* 2010;10:1141–1151.
19. Maiti K, Mukherjee K, Gantait A, Saha BP, Mukherjee PK. Curcumin-phospholipid complex: preparation, therapeutic evaluation and pharmacokinetic study in rats. *Int. J. Pharm.* 2007;330:155–163.
20. Das RK, Kasoju N, Bora U. Encapsulation of curcumin in alginate-chitosan-pluronic composite nanoparticles for delivery to cancer cells. *Nanomedicine.* 2010;6:153–160.
21. Gupta V, Aseh A, Rios CN, Aggarwal BB, Mathur AB. Fabrication and characterization of silk fibroin-derived curcumin nanoparticles for cancer therapy. *Int. J. Nanomed.* 2009;4:115–122.
22. Dinauer N, Balthasar S, Weber C, Kreuter J, Langer K, Brisen HV. Selective targeting of antibody-conjugated nanoparticles to leukemic cells and primary T-lymphocytes. *Biomaterials.* 2005;26:5898-5900.
23. Chopra M, Kaur P, Bernela M, Thakur R. Synthesis and optimization of streptomycin loaded chitosan-alginate nanoparticles. *Int. J. Sci. Tech Res.* 2012;1:31-34.
24. Martins AF, Bueno PVA, Almeida EAMS, Rodrigues FHA, Rubira AF, Muniz EC. Characterization of N-trimethyl chitosan/alginate complexes and curcumin release. *Int. J. Biol. Macromol.* 2013;57:174-184.
25. Varki A, Freeze EJ, Stanley P, Bertozzi C, Hart G, Etzler M. *Essentials of glycobiology.* Cold Spring Harb Lab. Press. 2008;62:770-779.
26. Angshuman B, Bhattacharjee SK, Mahanta R, Biswanth M, Bandyopadhaya SK. Alginate based nanoparticulate drug delivery for anti HIV drug lopinavir. *JGPT.* 2010;2:126-132.
27. Li P, Dai NY, Zhang PJ, Wang QA, Wei Q. Chitosan-alginate nanoparticles as a novel drug delivery system for nifedipine. *Int. J. Biomed. Sci.* 2008;4:221-228.
28. Rajaonarivony M, Vauthier C, Coiarraze G, Puisieux F, Couvreur P. Development of a new drug carrier made from alginate. *J. Pharm. Sci.* 1993;82:912-917.
29. Narashimhan B, Mallapragada SK, Peppas NA. *Encyclopedia of controlled drug delivery: release kinetics, data interpretation.* John Wiley and Sons, Inc: New York, pp 921;1999.
30. Hadjiioannou TP, Christian GD, Koupparis MA. *Quantitative calculations in pharmaceutical practice and research.* VCH Publishers: Inc, New York; 1993.
31. Higuchi T, Mechanism of sustained action medication, theoretical analysis of rate of release of solid drugs dispersed in solid matrices. *J. Pharm. Sci.* 1963;52(12):1145-1149.
32. Arhewoh MI, Okhamafe OA. An overview of site-specific delivery of orally administered protein/peptides and modelling considerations. *J. Med, Biomed. Res.* 2004;3:7-20.
33. Silvina AB, Maria CL, Claudio JS. In-vitro studies of diclofenac sodium controlled-release from biopolymeric hydrophilic matrices. *J. Pharm. Pharm. Sci.* 2002;5:213-219.
34. Ritger PL, Peppas NA. A simple equation for description of solute release II Fickian and anomalous release from swellable devices. *J. Control. Rel.* 1987;5:37-42.
35. Siepmann J, Peppas NA. Modeling of drug release from delivery systems based on hydroxypropyl methylcellulose (HPMC). *Adv. Drug Deliv. Rev.* 2001;48:139-157.

APPENDIX