

Green Synthesis, Characterization and Antioxidant activity of Silver Nanoparticles in Extracts of *Acorus calamus* and *Agaricus bisporus*.

ABSTRACT

Nanoparticles are in increasing commercial demand due to their wide applicability in various areas such as catalysis, chemistry, energy and medicine. Green chemistry is the best option to opt for the synthesis of nanoparticles.

Agaricus bisporus and *Acorus calamus* are used medicinally in ayurvedic medicines. The endeavor of the present work conducted was to determine antioxidant activity of the extracts made. Silver nanoparticles were synthesized by using aqueous extract of *Acorus calamus* & *Agaricus bisporus*. They were characterized by using UV spectrophotometer, Scanning Electron Microscopy (SEM) and Transmission Electron Microscopy (TEM).

Plant extracts were incubated with Silver Nitrate Solution (AgNO_3) and color change was observed as dark reddish brown. The presence of Ag nanoparticles was analyzed between the wavelengths 400-550 nm. The size of the nanoparticles was determined by SEM & TEM. The antioxidant activity was performed by DPPH (1, 1-diphenyl-2-picryl hydrazyl) free radical scavenging method for different solvents of *Acorus calamus* and *Agaricus bisporus* which showed that methanol extract on higher concentration possess better antioxidant potential when compared to standard. They exhibited strong DPPH free radical scavenging activity with 66.3 % and 59.2 % respectively for ascorbic acid equivalence. The absorbance for reducing power was found to be in increasing order with an increase in concentration.

The strongest antioxidant activity was displayed by methanolic extract, could be due to the presence of flavonoids and phenols. Also, the study reveals that the silver nanoparticles from methanol extract show better activity than the normal aqueous extract.

KEY WORDS: *Acorus calamus*, *Agaricus bisporus*, antioxidant activity, synthesis and characterization of silver nanoparticles.

INTRODUCTION

Medicinal Plants

Medicinal plants possess secondary metabolites which are the main sources of medicinal drugs having curative nature. 7500 species are being used as medicinal plants in India (Balakumbahan et al., 2010). Medicinal plant parts are commonly rich in phenolic compounds, such as phenolic acids, flavonoids, tannins and lignins. Multiple biological effects including the antioxidant activity are there in these compounds (Sharma et al., 2013). Antioxidants are widely used in dietary supplements and have been investigated for the prevention of diseases such as heart diseases, sickness and cancer (Dabelstein et al., 2007).

Acorus calamus (L.) family Araceae is a well known plant in Indian traditional medicines (Nadkarni et al., 2005) for centuries. *Acorus calamus* is a semi aquatic perennial, aromatic herb with creeping rhizomes (Tiwari et al., 2010), which has been used traditionally as a medicine and

also the powder of rhizome has spicy flavor. Its rhizome is used to treat gastrointestinal problems that include inflammation of stomach, flatulence, ulcers and anorexia. Other medicinal uses of *Acorus* are induction of sweating, treatment of stroke and treatment of rheumatoid arthritis.

Mushrooms have a long association with humankind and provide profound biological and economical impact. From ancient times, wild mushrooms have been consumed by man with delicacy, probably, for their taste and pleasing flavor (Das et al., 2010). They have rich nutritional value with high content of proteins, vitamins, fibers, trace elements and low/no calories and cholesterol (Agahar-Murugkar and Subbulakshmi et al., 2005; Wani et al., 2010). Edible mushrooms are important source of biologically active compounds (Rajewska and Balasinska et al., 2004) Edible mushrooms are used medicinally for diseases involving depressed immune function, cancer, allergies, fungal infection (Yashwant et al., 2012).

The development of reliable green process for the synthesis of silver nanoparticles is an important aspect of current nanobiotechnology research. Biosynthesis of nanoparticles is advantageous over chemical and physical methods as it is a cost effective and environmental friendly method (Sastry et al., 2004 and Mohanpuria et al., 2008), and it is not necessary to use high pressure, energy, temperature and toxic chemicals. Plants provide a better platform for nanoparticle synthesis as they are free from toxic chemicals as well as provide natural capping agents. Moreover, use of plant extracts also reduces the cost of microorganism isolation and culture media enhancing the cost competitive feasibility over nanoparticle synthesis by microorganisms.

OBJECTIVE

Present study was aimed to prepare aqueous and methanolic extracts of *Agaricus bisporus* and *Acorus calamus*. Prepared extracts were screened for the presence of the antioxidant activity. Study also focused on the biosynthesis of silver nanoparticles of both aqueous and methanolic extracts along with their free radical scavenging activities.

MATERIALS & METHODS

Collection of plant materials

Materials used in the present study were fruiting bodies of *Agaricus bisporus* and *Acorus calamus* procured from TERI, Gurugram, Haryana, India.

Collected samples were identified and authenticated by the taxonomist of the same department.

Bacterial Strains

The bacterial strains of *Escherichia coli* (DH5α), *Bacillus amyloliquefaciens*, *Staphylococcus aureus* and *Pseudomonas aeruginosa* were obtained from Helix BioGenesis Pvt. Ltd., Noida, U.P., India. They were sub cultured freshly in Nutrient Broth and used further for research work.

Sample preparation

Plant samples were washed, dried and crushed by an ordinary grinder (Philips HL 7720) to make fine powder. The 50g of dried rhizome of *A. Calamus* and *A. bisporus* was weighed in weighing balance (High Precision Balance) and placed in a Soxhlet extractor (Lin et al., 1999) containing 800ml of methanol and pouch of extracts for 24hrs to 48hrs (22 cycles). Then obtained methanol extracts was evaporated to dryness and extract amount was measured. Extract was stored for the further use.

The 50g of rhizome crushed powder was dissolved in 500ml of distilled water to form crude extract by maceration method by boiling continuously for 30minutes in water bath (Thermo Scientific). The conical flasks of the extracts were covered by cotton plugs to avoid the evaporation. The extracts were placed in shaking incubator at 250rpm for 48hrs. After shaking they were filtered with muslin cloth and with filter paper twice. Prepared crude extracts were evaporated to dryness; amount was measured (Siddhuraju et al., 1996) and was stored at 4°C (Sharma & Nagar et al., 2015).

Synthesis of silver nanoparticles

For the synthesis of silver nanoparticles (AgNPs), 50ml stock solution of 2mm AgNO₃ was prepared in distilled water. 1ml of aqueous extract of *A. calamus* and *A. bisporus* each was added to 9ml of stock solution of AgNO₃ in conical flask. The mixture was stirred continuously for 5-10 minutes and then incubated in dark room, at 37°C under static condition. Suitable controls were maintained throughout the experiment. Reduction of silver nitrate to silver ions was confirmed by the color changes to light yellow color to brown color. Simultaneously, the positive control was maintained with the extract and de-ionized water used as negative control containing only silver nitrate solution (Narasimha et al., 2011).

CHARACTERIZATION:

1. **UV-Visible spectra analysis:** The silver nanoparticles were characterized by UV-Vis spectrophotometer (Hitachi High Technologies), one of the most widely used techniques for structural characterization of silver nanoparticles (Sun et al., 2001). UV-Visible absorption spectrophotometer with a resolution of 2nm between 300 to 700nm was used. (Ahmed et al., 2003).
2. **Scanning Electron Microscopy (SEM):** SEM analysis was done (Hitachi S-4500 SEM). For SEM, the silver nanoparticle synthesized using *A. calamus* and *A. bisporus* extracts was prepared on the slide, one drop of sample was taken on a glass slide and was dried in an incubator. After the slide was prepared, the sample was coated with gold for 3 mins to make it conductive. And then the SEM images were taken to study the size and morphology of the nanoparticle formed.

3. Transmission Electron Microscopy (TEM): Morphological and structural studies were investigated using HR-TEM that allows the imaging of the crystallographic structure of a sample at an atomic scale. HR-TEM was utilized to characterize the particles and their sizes and distributions by taking micrograph from drop coated film of silver nanoparticles (Tecnai G2-20 Transmission electron microscope, FEI Company, Netherlands). The specimen was suspended in distilled water, dispersed ultra-sonically to separate individual particles and one or two drops of suspension deposited onto holey-carbon coated copper grids and dried under infra-red lamp (Jha et al., 2009).

ANTIOXIDANT ASSAY

1. Electron transfer assay

Total Flavonoid Content (TFC) and Total Phenolic Content (TPC) were assayed to determine the oxidants which were reduced by transfer of electron from antioxidant (oxidized).

a. Total Flavonoid Content

Number of flavones that were present in extracts was determined by Aluminium Chloride Spectrophotometric method. About 0.1ml of extract or Quercetin standard 10-100 μ g/ml, 1.5ml of methanol, 0.1ml Aluminium chloride (10%), 0.1ml Potassium acetate (1M) and 2.8ml of distilled water were added and mixed well. Sample blank was prepared by replacing sample with distilled water or solvent and absorbance was measured at 417nm. Standard calibration plot was made to determine the concentration of flavonoids in the extracts. The concentrations of flavonoids in the extracts were calculated from the calibration plot and were expressed in mg QE/ g of extracts (Maurya et al., 2011 & Sharma et al., 2017).

b. Total Phenolic Content

Flavonoids are polyphenolic compounds. So, TPC was determined by Folin-Ciocalteu method in order to quantify the polyphenolic Flavonoids. 0.1ml of extracts or Quercetin standard (10-100 μ g/ml) and 0.1ml of Folin-Ciocalteu reagent (0.5N) was added and incubated at room temperature for 30min. About 2.5ml of 20% saturated sodium carbonate was added in to the solution and further incubated for 30min. After incubation, the absorbance was measured at 760nm against blank reagent. The standard calibration plot was made to determine the concentration of polyphenolic components in the extracts were calculated from the calibration plot and were expressed in mg QE of phenol g⁻¹ of extracts (Maurya et al., 2011 & Sinha et al., 2015).

2. DPPH Assay

DPPH (2, 2-diphenyl picryl hydrazyl) is a commercially available stable free radical, which is purple in color. The antioxidant molecules present in the herbal extracts, when incubated, react with DPPH and convert it into di-phenyl hydrazine, which is yellow in color. The degree of discoloration of purple to yellow was measured at 520nm, which is a measure of scavenging potential of plant extracts. 10 μ l of plant extract was added to 100 μ l of DPPH solution (0.2mM

DPPH in methanol) in a microtitre plate (Mensor et al., 2001). The reaction mixture was incubated at 25°C for 5 minutes, after that the absorbance was measured at 520nm. The DPPH with corresponding solvents (without plant material) serves as the control. The methanol with respective plant extracts serves as blank. The DPPH radical scavenging activity of the plant extract was calculated as the percentage inhibition.

DPPH scavenging effect (%) or Percent inhibition = $A_0 - A_1 / A_0 \times 100$.

Where A_0 was the Absorbance of control reaction and A_1 was the Absorbance in presence of test or standard sample (Achola et al., 1998).

3. Reducing power assay

Ferric reducing power of extracts was also determined (Oyaizu et al., 1986). One ml of extracts at various concentrations 25 - 2000µg/ml was respectively added to phosphate buffer (2.5ml, 0.2M, pH 6.6) and potassium ferricyanide (2.5ml, 1%) followed by mixing and incubating at 50°C for 20min. Then, Tri Chloro Acetic Acid (TCA) (2.5ml, 10 %) was added to the mixture and centrifuged at 3000rpm for 10min. 2.5ml of the supernatant was collected and mixed with 2.5ml of distilled water followed by the addition of ferric chloride (0.5ml, 0.1%), vortexed and the absorbance of the mixtures was read at 700nm.

RESULTS & DISCUSSION

Biosynthesis of silver nanoparticles

Synthesis of AgNPs using *A. bisporus* and *A. calamus* extract was observed (Figure 1). When *A. calamus* and *A. bisporus* extract of different concentrations was subjected to aqueous solution of 2mm silver nitrate, a gradual change of color was observed after 12hrs. This change of color was due to the formation of AgNPs. The formation of reduced AgNPs was further characterized by UV-Vis spectrophotometer.

UV Spectra Analysis

It is well known that AgNPs exhibit yellowish brown color in aqueous solution due to excitation of surface Plasmon vibrations in AgNPs (Shankar *et al.*, 2004). As the extract was mixed in the aqueous solution of the silver ion complex, it started to change the color from watery to yellowish brown due to reduction of silver ion which indicated formation of AgNPs. It is generally recognized that UV-Vis spectroscopy can be used to examine size and shape controlled nanoparticles in aqueous suspensions (Wiley *et al.*, 2006). The extracellular biosynthesis of AgNPs from *A. bisporus*, *Ganoderma lucidum* and *Pleurotus florida* was observed at the maximum absorbance peak 420nm, 420nm and 435nm respectively (Sujatha et al., 2013, Singh et al., 2013 and Balahanmuga et al., 2013). Similarly, the peak located between 420nm-460nm was observed for AgNPs prepared using the *A. calamus* extracts and 420nm-430nm in *A. bisporus* samples indicating the production of AgNPs from the extracts.

Scanning Electron Microscopy

SEM was employed to analyze the shape of the AgNPs that were biosynthesized. SEM analysis shows that these two plant (*Acorus calamus* and *Agaricus bisporus*) extracts have tremendous capability to synthesize AgNPs, which were roughly spherical in shape and were uniformly distributed. Characterization of AgNPs were observed under SEM revealed that nanoparticles varied shaped (spherical and irregular) with size in the range of 50-200µm (Figure 3-10). Spherical AgNPs aggregates were reported by (Nithya and Ragunathan et al., 2009) that synthesized AgNPs by *Pleurotus sajorcaju* of size range 5-50µm and (Narasimha et al., 2011) who reported that their size range 5-50µm AgNPs by *A. bisporus*, while (Karwa et al., 2011) who obtained AgNPs prepared by *Ganoderma lucidium* showed the poly disperse nature of their nanoparticles with size range (10-70µm). The surfaces of the aggregates were rough. The particles are more or less spherical in sizes and their range is of 45-80µm.

Transmission Electron Microscopy

Biologically synthesized AgNPs was deposited on a carbon coated TEM grid and processed. The micrograph showed nanoparticles with variable shape, most of them were spherical with some others having occasionally triangular and linear shape. The size of the particles was from 15 to 25nm (Figure 11-18). Majority of the AgNPs were scattered, with only a few showing aggregates of varying sizes as observed under TEM. AgNPs are apparently spherical particles, sized range (4.5-35nm) poly dispersed by TEM. The peak at 430nm indicates that AgNPs have spherical form (Sudhakar et al., 2014).

Anti Oxidant Assay

Solvents like distilled water and methanol were used to extract out the flavonoids & phenol and reducing power ability & DPPH radical scavenging activity from the sample. After preparation of extracts by Maceration method, the extracts were phytochemically screened in order to check the presence of different secondary metabolites including flavonoids and phenols. Plant phenols constitute the major group of compounds that act as primary antioxidant (Hatano et al., 2016). To determine the antioxidant content in the extract, electron transfer assay were assayed, such as TFC and TPC. It was found from the study (Table 1 and 3) that methanolic extract *A. calamus* has maximum amount of phenol and flavonoids (19670mg and 13690mg of QE/ g of extract) & silver nano extract showed 3380mg of QE/g of extract, whereas in *A. bisporus* of aqueous extract has maximum amount of phenol and flavonoids (6860mg and 7640mg of QE/g of extract) and silver nano extract in methanolic extract has showed 4030mg of QE/g of extract. Figure 21 and 22 demonstrates TFC, very less in silver nano extract of plants.

DPPH is a protonated radical having the characteristic absorption maxima at 517nm which decreases with the scavenging of the proton radical by natural plant extracts. Hence, DPPH finds applications in the determination of the radical scavenging activity of plant materials (Jun et al., 2004). DPPH scavenging ability was screened in both aqueous and methanolic extracts (Figure 23 and 24). In methanolic extract, *A. calamus* and *A. bisporus* showed a strong inhibition of up to 65.1% and 59.2 % respectively followed by the aqueous extract with 4.1% and 19.1 % inhibition respectively. Whereas the silver nano aqueous extract of *A. calamus* and *A. bisporus*, showed 23.8% and 40% inhibition and methanolic extract showed the maximum inhibition- 66.3% and 19.1% respectively. Silver nano extracts of *A. calamus* and *A. bisporus* possessed higher DPPH radical scavenging in methanol. Reducing power of both the extracts increased with an increase in concentration. The reducing power of the extracts was found to be dose dependent (Figure 25

and 26). The methanolic extract of *A. calamus* and *A. bisporus* and its silver nano extract showed more reductive ability than the aqueous extract, which was capable for neutralizing the free radical.

In the present study, we found that plants of rhizomes were good source for the synthesis of silver nanoparticles. It has many advantages such as, ease with which the process can be scaled up, economic viability and to obtain smaller particle size. In conclusion, the *A. calamus* & *A. bisporus* aqueous extract has shown potential for extra cellular synthesis of fairly mono dispersed AgNPs in the range of 10nm to 20nm. AgNPs were synthesized successfully by green synthesis method (from *A. calamus* and *A. bisporus* plant extract). The detail characterization of the nanoparticles was carried out using UV-Vis spectroscopy, SEM and TEM. In SEM and TEM image analysis, the average particle size was found to be 15nm and 30nm. The results confirmed the reduction of silver nitrate to AgNPs with high stability and without any impurity.

The objective of the study was to determine the antioxidant and free radical scavenging potential of the whole plant, *A. calamus* and *A. bisporus* and also to provide a comparative analysis between the methanolic and aqueous extracts of the plants and its silver nano extract as a free radical scavenger to specify the extract with a better scavenging potential. According to the findings, the methanol extract showed the highest amount of phenolics, reducing ability and free radical scavenging activity as compared to the flavonoids and the aqueous extracts. Studies on the whole plant also revealed that antioxidant property of the plant is in no way lesser than its root and rhizomes.



Figure: 1 and 2 - Synthesis of AgNPs in *A. calamus* and *A. bisporus* plant extracts.





Figure: 3, 4, 5 and 6- Characterized AgNPs of aqueous and methanolic extract of *A. bisporus* with different concentration (0.2g/ml and 0.4g/ml) by SEM analysis.






Figure: 7, 8, 9 and 10- Characterized AgNPs of aqueous and methanolic extracts of *A. calamus* with different concentration (0.2g/ml and 0.4g/ml) by SEM analysis.




Figure: 11, 12, 13 and 14- Characterized AgNPs of aqueous and methanolic extracts of *A. bisporus* with different concentration (0.2g/ml and 0.4g/ml) by TEM analysis.





Figure: 15, 16, 17and 18- Characterized AgNPs of aqueous and methanolic extracts of *A. calamus* with different concentration (0.2g/ml and 0.4g/ml) by TEM analysis.



Graph 1: Quercetin standard curve for TPC

Table 01: TPC in *A. calamus* and SN extract from methanol and distilled water.

Extract	0.2 gm/ml	0.4 gm/ml
	mg QE/g of extract	mg QE/g of extract
Aqueous <i>A. calamus</i>	9220	18510
Aqueous SN <i>A. calamus</i>	697	763
Methanolic <i>A. calamus</i>	10050	19670
Methanolic SN <i>A. calamus</i>	2130	3380




Figure 19: TPC of *A. calamus* and its SN extract.

Table 02: TPC in *A. bisporus* and SN extract from methanol and aqueous.

Extract	0.2 gm/ml	0.4 gm/ml
	mg QE/g of extract	mg QE/g of extract
Aqueous <i>A. bisporus</i>	6020	6860
Aqueous SN <i>A. bisporus</i>	290	670
Methanolic <i>A. bisporus</i>	3120	5980
Methanolic SN <i>A. bisporus</i>	2840	4030





Figure 20: TPC of *A. bisporus* and its SN extract.



Graph 2: Quercetin standard curve for TFC

Table 03: TFC in *A. calamus* and SN extract from methanol and aqueous.

Extract	0.2 gm/ml	0.4 gm/ml
	mg QE/g of extract	mg QE/g of extract
Aqueous <i>A. calamus</i>	1710	2700
Aqueous SN <i>A. calamus</i>	170	210
Methanolic <i>A. calamus</i>	2680	13690
Methanolic SN <i>A. calamus</i>	150	270

Total Flavonoid Count in *A. calamus* and its SN extract




Figure 21: TFC of *A. calamus* and its SN extract

Table 04: TFC in *A. bisporus* and SN extract from methanol and aqueous.

Extract	0.2 gm/ml	0.4 gm/ml
	mg QE/g of extract	mg QE/g of extract
Aqueous <i>A. bisporus</i>	7210	7640
Aqueous SN <i>A. bisporus</i>	140	170
Methanolic <i>A. bisporus</i>	281	1740
Methanolic SN <i>A. bisporus</i>	180	310




Figure 22: TFC of *A. bisporus* and its SN extract

Table 05: DPPH Free Radical Scavenging in *A. calamus* and its SN extract from methanol and aqueous.

Extract	0.2 gm/ml DPPH AEAC % Inhibition	0.4 gm/ml DPPH AEAC % Inhibition
Aqueous <i>A. calamus</i>	4.1	3.1
Aqueous SN <i>A. calamus</i>	12.1	23.8
Methanolic <i>A. calamus</i>	65.1	3
Methanolic SN <i>A. calamus</i>	66.3	38.5




Figure 23: DPPH Free Radical Scavenging in *A. calamus* and SN extract

Table 06: DPPH Free Radical Scavenging in *A. bisporus* and its SN extract from methanol and aqueous.

Extract	0.2 gm/ml DPPH AEAC % Inhibition	0.4 gm/ml DPPH AEAC % Inhibition
Aqueous <i>A. bisporus</i>	19.1	5
Aqueous SN <i>A. bisporus</i>	40	38
Methanolic <i>A. bisporus</i>	59.2	49.6
Methanolic SN <i>A. bisporus</i>	19.1	16.2




Figure 24: DPPH Free Radical Scavenging in *A. bisporus* and its SN extract.

Table 07: Ferric Reducing Power in *A. calamus* and its SN extract from methanol and aqueous.

Extract	0.2 gm/ml FRP (mg/ GAE/10 g of sample)	0.4 gm/ml FRP (mg/ GAE/10 g of sample)
Aqueous <i>A. calamus</i>	2.3	2.8
Aqueous SN <i>A. calamus</i>	0.83	1.5
Methanolic <i>A. calamus</i>	3.7	5.3
Methanolic SN <i>A. calamus</i>	1.8	2.6




Figure 25: Ferric Reducing Power in *A. calamus* and its SN extract

Table 08: Ferric Reducing Power in *A. bisporus* and its SN extract from methanol and aqueous.

Extract	0.2 gm/ml FRP (mg/ GAE/10 g of sample)	0.4 gm/ml FRP (mg/ GAE/10 g of sample)
Aqueous <i>A. bisporus</i>	0.48	0.76
Aqueous SN <i>A. bisporus</i>	0.22	0.24
Methanolic <i>A. bisporus</i>	0.72	1.2
Methanolic SN <i>A. bisporus</i>	0.25	0.4




Figure 26: Ferric Reducing Power in *A. bisporus* and its SN extract

CONCLUSION

Our current findings suggest that the extracts of the whole plant is equally useful as a source of natural antioxidants with subsequent health benefits. *Acorus calamus* and *Agaricus bisporus* silver nano extracts can be utilized as natural, cost effective and eco friendly attributes. We believe that the silver nano extracts has great potential for applications in catalysis, biomedical, and pharmaceutical industries.

ABBREVIATIONS:

Agaricus bisporus: *A. bisporus*

Acorus calamus: *A. calamus*

Total Phenolic Content: TPC

Total Flavonoid Content: TFC

Scanning Electron Microscopy: SEM

Transmission Electron Microscopy: TEM

Silver Nitrate: AgNO_3

Silver nano: SN

Silver Nano Particles: AgNPs

410

REFERENCE

- 411 1. Achola, KJ, *et al*, "Bronchodilating and uterine activities of *Ageratum conyzoides*
412 extract", Pharmaceutical Biology, 36(2), 1998, 93-96.
- 413 2. Agrahar-Murugkar D, Subbulakshmi, G (2005). Nutritional value of edible wild
414 mushrooms collected from the Khasi hills Meghalaya. Food Chem. 89:599-603.
- 415 3. Ahamed. M, Alsalhi. M. S, Siddiquy. M. K. J. (2010) Green synthesis, Characterization
416 and evaluvation of Biocompatibility of silver nanoparticles. J. Clin. Chim. Acta. 441.
- 417 4. B. J. Wiley, S. H. Im, J. McLellan, A. Siekkinen. Y. Xia ., J. Phys. Chem. B .2006,(110),
418 15666
- 419 5. D.Singh, Vandana Rathod, Shivaraj Ninganagouda, Jyothi Herimath, Perma Kulkarni.
420 "Biosynthesis of silver nanoparticles by endophytic fungi *Penicillium* sp. isolated from
421 *Curcuma longa* (turmeric) and its antibacterial activity against pathogenic gram negative
422 bacteria" journal of pharmacy research, Vol.7, (2013), pp. 448-453.
- 423 6. Dabelstein, Werner; Reglitzky, Arno; Schütze, Andrea; Reders, Klaus (2007).
424 "Automotive Fuels". Ullmann's Encyclopedia of Industrial Chemistry.
425 doi:10.1002/14356007.a16_719.pub2. ISBN 3527306730
- 426 7. Das K (2010). Diversity and conservation of wild mushrooms in Sikkim with special
427 reference to Barsey Rhododendron Sanctuary. NeBIO. 1(2):1-13.
- 428 8. Hatano T, Edamatsu R, Mori A, Fujita Y, Yasuhara E (1989). Effects of tannins and
429 related polyphenols on superoxide anion radical and on 1,1 diphenyl-2-picryl hydrazyl.
430 Chem. Pharm. Bull.37,2016-23.
- 431 9. Jha.A.K, Prasad.K, Kulkarni.A.R,(2009) Synthesis of TiO2 nanoparticles using
432 microorganisms. J. Colloids surf. B: Biointerf. 71: 226-229.
- 433 10. Jun M, Tohru U, Jianzhang L, Takeshi F (2004).Identification and evaluation of
434 antioxidant activities of bamboo extracts. For Stud China, 6: 1-5.
- 435 11. Karwa, A; Gaikwar, S. and Rai, M.(2011). Mycosynthesis of silver nanoparticles using
436 Lingzhi or Reishi medicinal mushroom, *Ganoderma lucidum* (W. Curt.:Fr.) P. Karst. and
437 their role as antimicrobials and antibiotic activity enhancers, Int. J. Med.
438 Mushroom,13(5): 483- 491.
- 439 12. Lin J ,Opuku AR, Geheeb-Keller M (1999): Preliminary Screening of some traditional
440 Zulu medicinal plants for anti-inflammatory and antimicrobial activities. J.
441 Ethanopharmacol. 68: 267-264.
- 442 13. Maurya, U.; Srivastava, S. Traditional Indian Herbal Medicine Used As Antipyretic,
443 Antiulcer, Anti-Diabetic And Anticancer: A Review. International Journal Of Research
444 In Pharmacy And Chemistry. 1(4): 1152-1159; 2011.
- 445 14. Mensor LL, Meneze FS, Leitao et al., (2001).Screening of Brazilian plant extracts for
446 antioxidant activity by the use of DPPH free radical method. Phytother.Res.15, 127-130.
- 447 15. Mohanpuria, P., Rana, N.K., Yadav, S.K., J Nanopart Res.,2008, 10,507.
- 448 16. N.Tiwari, A. Chaudhary, A. Mishra & G. Bhatt., *International Journal of chemical and*
449 *Analytical Science.*, 2010, 1(9), 211.
- 450 17. Nadkarni KM (2005), Indian Plants and Drugs with their medicinal properties and Uses,
451 New Delhi: Srishti Book Distributors; p, 16-7.
- 452 18. Narasimha B. Parveen.K. Mallikarjuna, B. Deva Prasad Raju. 2011. Mushrooms
453 (*Agaricus bisporus*) mediated biosynthesis of silver nanoparticles, characterization and
454 their antimicrobial activity. International Journal of Nano Dimentions.2 (1); 29-36.

19. Narasimha, G.; Praveen, B.; Mallikarjuna, K.; Raju, B. B. D.; (2011) Mushrooms (*Agaricus bisporus*) mediated biosynthesis of silver nanoparticles, characterization and their antimicrobial Activity Int. J. Nano Dim., 2(1): 29-36.
20. Nithya, R. and Ragunathan, R. (2009). Synthesis of silver nanoparticle using *Pleurotus Sajor Caju* and its antimicrobial activity. Digest Journal of Nanomaterials and Biostructures 4(4) :623-629.
21. Oyaizu M Studies on products of browning reaction prepared from glucoseamine. Jpn J Nutr 1986; 44: 307-315.
22. P. Balahanmuga, S. Santhosh, H. Giyaullah, M. D. Balakumaran, P. T. Kalaichelvan. "Mycosynthesis, Characterisation and Antibacterial activity of Silver nanoparticles from *Microsporus xanthopus*: A Macro Mushroom." Int. J. Inov. Res. in Sci. Eng. & Tech. Vol. 2, No. 11, (2013).
23. R. Balakumbahan, K. Rajamani & K. Kumanan., *Journal of Medicinal Plants Research*., 2010, 4(25), 2740.
24. S. S. Shankar, A. Rai, B. Ankamwar, A. Singh, A. Ahmad, M. Sastry., *Nat. Mater.* 2004, (3), 482
25. S. Sujatha, Tamilselvi, K. Subha. and A. Panneerselvam. "Studies on biosynthesis of silver nanoparticles using Mushroom and its antibacterial activities". *International Journal of Current Microbiology and Applied Sciences*. Vol. 2. No. 12, (2013), pp. 605-614
26. Sastry, M., Ahmad, A., Khan, M. I., and Kumar, R., *Microbial nanoparticle production*, in *Nanobiotechnology*, ed. by Niemeyer CM and Mirkin CA. Wiley-VCH, Weinheim., 2004, 126.
27. Sharma SK, Singh Lalit, Singh Suruchi, A review on medicinal plants having antioxidant potential, *Indian J of Research in Pharmacy and Biotechnology*, Vol 1(3) May-Jun, 2013, PP404-409.
28. Sharma Y, Dua D and Srivastva SN: Comparative study of different parts of *Azadirachta indica* (neem) plant on the basis of anti-bacterial activity, phytochemical screening and its effect on rat PC-12 (Pheochromocytoma) cell line. *International Journal of Biotechnology and allied fields* 2014; 2 (7):144 – 154.
29. Sharma Y, Dua D and Srivastva SN: Comparative study of different parts of *Azadirachta indica* (neem) plant on the basis of anti-bacterial activity, phytochemical screening and its effect on rat PC-12 (Pheochromocytoma) cell line. *International Journal of Biotechnology and allied fields* 2014; 2 (7):144 – 154.
30. Sharma Y, Nagar A and Shukla S: Antibacterial activity and phytochemical screening of *Adenium obesum* (Desert rose) leaf. *International Journal of Pharmaceutical and BioScience* 2015; 6(3):85-92.
31. Siddhuraju, P.; Vijayakumar, K. and Janardhanan, K 1996. *Food. Chem.* 57(3) 385 – 391.
32. Sinha N, Dua D, Wadhwa D. Antioxidant activity, free radical scavenging capacity and phytochemical screening of some selected Indian plants of medicinal importance. *International journal of Innovative Pharmaceutical Sciences and Research* 2015; 3: 151-163.
33. Sudhakar, T.; Nanda, A.; George, S.; Janani, B. S.; Evans, M. D. and Markose, T. K. (2014). Synthesis of Silver Nanoparticles from Edible Mushroom and Its Antimicrobial Activity against Human Pathogens. *Sathyabama University, Jeppiaar nagar, Rajiv Gandhi Salai Int. J. Pharm. Tech. Research*, 6(5) :1718-1723.

- 500 34. Sun, Y. P., Apornjitjawait, P. And Meziani, M. J. (2001) Preparation of silver
501 nanoparticles via rapid expansion of water in carbon dioxide micro emulsion into
502 reductant solution. J. Langmuir.17:5707-5710.
- 503 35. Wani BA, Bodha RH, Wani AH (2010). Nutritional and medicinal importance of
504 mushrooms. J. Med. Plants Res. 4(24): 2598-2604.
- 505 36. Wasser SP, Weis AL (1999). Medicinal properties of substances occurring in higher
506 basidiomycetes mushrooms: current perspectives (review). Int. J. Med. Mushrooms. 1:31-
507 62
- 508 37. Yashvant Patel, Ram Naraian and V.K Singh, Medicinal Properties of *Pleurotus* Species
509 (Oyster Mushroom): A review World Journal of Fungal and Plant Biology, 2012; 3 (1):
510 01-12.
- 511
- 512